

## PRODUCT DATA SHEET

# SikaForce®-818 L07

High performance non-sagging structural adhesive

**TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)**

Properties	Component A SikaForce®-818 L07	Component B SikaForce®-050
Chemical base	Polyols	Isocyanate derivatives
Color (CQP001-1)	White	Brown
	mixed	Beige
Cure mechanism	Polyaddition	
Density (uncured)	1.25 g/cm <sup>3</sup>	1.22 g/cm <sup>3</sup>
	mixed (calculated)	1.24 g/cm <sup>3</sup>
Mixing ratio	by volume 100 : 45	
Viscosity (CQP029-4)	25 mm PP, d = 1 mm, 10 s <sup>-1</sup>	80 Pa·s <sup>A</sup>
		15 Pa·s <sup>A</sup>
Application temperature	10 – 35 °C	
Shore D hardness (CQP023-1 / ISO 48-4)	75 <sup>A, B</sup>	
Tensile strength (CQP036-2 / ISO 527)	30 MPa <sup>A, B, C</sup>	
Elongation at break (CQP036-2 / ISO 527)	3 % <sup>A, B, C</sup>	
E-Modulus (CQP036-2 / ISO 527)	2 500 MPa <sup>A, B, C</sup>	
Tensile lap-shear strength (CQP046-9 / ISO 4587)	20 MPa <sup>A, B, D</sup>	
Glass transition temperature (CQP509-1 / ISO 6721)	55 °C <sup>B</sup>	
Shelf life	drum	12 months
	cans and pails	9 months
	cartridges	12 months

CQP = Corporate Quality Procedure

C) tested at 2 mm/min

A) 23 °C / 50 % r. h.

D) adhesive layer: 25 x 12.5 x 3 mm

B) cured for 28 days at 23 °C

**DESCRIPTION**

SikaForce®-818 L07 is a structural 2-component polyurethane adhesive, which cures at room temperature. It is designed for bonding composite components. The adhesive is characterized by fast curing and strength build-up. While uncured, it has very good non-sag and compressibility behavior.

**PRODUCT BENEFITS**

- Very good non-sag behaviour
- Short curing time
- High strength and modulus for structural bonding applications
- Low smell
- Does not contain solvents or PVC

**AREAS OF APPLICATION**

SikaForce®-818 L07 is used for various bonding applications in the wind turbine manufacturing process, e.g. the attachment of mounting parts, lightning protection etc. This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.

**PRODUCT DATA SHEET**

SikaForce®-818 L07

Version 04.01 (07 - 2023), en\_CORP

012104588180001000

*This document serves only as an illustration of a Sika product during the sales process and therefore, is not binding for local sale. Please consult the local country product data sheet for specific terms and conditions.*

## CURE MECHANISM

The curing of SikaForce®-818 L07 takes place by a chemical reaction of the two components. Higher temperatures speed up and lower temperatures slow down the curing process. The final glass transition temperature, as well as the tensile and shear strengths, may be increased with higher curing temperature.

## CHEMICAL RESISTANCE

In case of chemical or thermal exposure, it is required to conduct project related testing.

## METHOD OF APPLICATION

### Surface preparation

Surfaces must be clean, dry and free from grease, oil, dust and contaminants. After the cleaning process, a physical or chemical pretreatment might be required, depending on surface and type of material. The type of pretreatment must be determined by tests.

### Application

For the cartridge application use a suitable manual or a compressed air piston-type cartridge dispenser.

To ensure good mixing quality the defined static mixer is to be used.

Extrude adhesive without mixer to equalize the filling levels. Attach the mixer and dispose the first few cm of the bead before the application.

SikaForce®-818 L07 can also be processed from pails with adequate 2-component equipment. For automated applications, contact the System Engineering Department of Sika Industry.

### Removal

Uncured SikaForce®-818 L07 may be removed from tools and equipment with Sika® Remover-208. Once cured, the material can only be removed mechanically.

Hands and exposed skin have to be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water.

Do not use solvents on skin.

## STORAGE CONDITIONS

SikaForce®-818 L07 has to be kept between 10 °C and 30 °C in a dry place. Do not expose it to direct sunlight or frost. After opening of the packaging, the content has to be protected against humidity.

The lowest allowed temperature during transportation is -20 °C for max. 7 days.

## FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets

## PACKAGING INFORMATION

### SikaForce®-818 L07 (A)

Can	1 kg
Pail	20 kg
Drum	240 kg

### SikaForce®-050 (B)

Can	0.45 kg
	1 kg
	5 kg
Pail	25 kg
Drum	250 kg

### SikaForce®-818 L07 (A+B)

MixCan	(6x) 1.45 kg
--------	--------------

Coaxial cartridge	195 ml
Mixer: MCH 10-24T by Medmix	

Dual cartridge	400 ml
Mixer: MFH 10-24T by Medmix	

## BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

## DISCLAIMER

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

## PRODUCT DATA SHEET

SikaForce®-818 L07  
Version 04.01 (07 - 2023), en\_CORP  
012104588180001000

Sika Services AG  
CH-8048, Zurich  
Switzerland  
Tel. +41 58 436 40 40  
Email: ctd@ch.sika.com  
www.sika.com/industry

